

Design and optimization of electrochemical cell potential for hydrogen gas production

Nawar K. Al-Shara^a, Farooq Sher^{b,*}, Sania Z. Iqbal^c, Oliver Curnick^d, George Z. Chen^{a,e}

^a *Department of Chemical and Environmental Engineering, University of Nottingham, University Park, Nottingham NG7 2RD, UK*

^b *School of Mechanical, Aerospace and Automotive Engineering, Faculty of Engineering, Environmental and Computing, Coventry University, Coventry CV1 2JH, UK*

^c *Department of Biochemistry, University of Agriculture, Faisalabad 38000, Pakistan*

^d *Institute for Future Transport and Cities, Coventry University, Coventry CV1 5FB, UK*

^e *Department of Chemical and Environmental Engineering, Faculty of Science and Engineering, University of Nottingham Ningbo China, University Park, Ningbo 315100, China*

*Corresponding author.

E-mail address: Farooq.Sher@coventry.ac.uk, Farooq.Sher@gmail.com (F. Sher);

Tel.: +44 (0) 24 7765 7754

Highlights

- The efficiency of electrochemical cell for steam splitting through electrolysis of eutectic molten hydroxide is evaluated.
- 54 combinations of electrochemical cell are tested with cathode, anode and different operating variable for H₂ gas production.
- Current efficiency @ stainless steel anode and Ni, Pt and St.st cathodes at 300 °C is 70 to 90%.
- Current efficiency @ graphite anode and Ni, Pt and St.st cathode at 300 °C is 70 to 80%.
- Splitting steam electrolysis is proved a promising alternative to current technology for H₂ gas production.

29 **Abstract**

30 This study deals with the optimization of best working conditions in molten melt for the production
31 of hydrogen (H₂) gas. Limited research has been carried out on how electrochemical process occurs
32 through steam splitting via molten hydroxide. 54 combinations of cathode, anode, temperature and
33 voltage have been investigated for the optimization of best working conditions with molten
34 hydroxide for hydrogen gas production. All these electrochemical investigations were carried out
35 at 225 to 300 °C temperature and 1.5 to 2.5 V applied voltage values. The current efficiency of
36 90.5, 80.0 and 68.6% has been achieved using stainless steel anodic cell with nickel, stainless steel
37 and platinum working cathode respectively. For nickel cathode, an increase in the current directly
38 affected the hydrogen gas flow rate at cathode. It can be hypothesized from the noted results that
39 increase in current is directly proportional to operating temperature and applied voltage. Higher
40 values were noted when the applied voltages increased from 1.5 to 2.5 V at 300 °C, the flow rate
41 of hydrogen gas increased from 1.5 to 11.3 cm³ min⁻¹, 1.0 to 13 cm³ min⁻¹ in the case of electrolysis
42 @ stainless steel and @ graphite anode respectively. It is observed that the current efficiency of
43 stainless steel anodic cell was higher than the graphite anodic cell. Therefore, steam splitting with
44 the help of molten salts has shown an encouraging alternate to current methodology for H₂ fuel
45 production.

46

47 **Keywords:** Sustainable energy; Splitting steam; Electrolysis; Hydrogen gas production;
48 Electrochemical cell and Variable cathodes.

49

50 **1. Introduction**

51 Hydrogen (H₂) has received focus among several alternative fuel sources because it provides
52 principal advantages and fulfils ideal fuel requirements. Hydrogen fuel is the same as
53 electrochemical energy in terms of being a high-efficiency energy carrier. When it is used, it can
54 lead to zero or near-zero emissions. For this reason, recently, many researchers and organizations
55 have propagated H₂ fuel to minimise global warming hazards. The most studied technique for the
56 production of H₂ gas from water is through the electrolysis of aqueous alkaline hydroxide solutions
57 [1].

58
59 The published studies [2,3] clearly mention that 19 methods exist in for hydrogen gas production,
60 including plasma arc decomposition, dark fermentation, coal gasification, biophotolysis, artificial
61 photosynthesis, electrolysis and others. It was also concluded that among all electrical hydrogen
62 production via electrolysis gives good energy efficiency as well as with the lowest cost rate.
63 Electrolysis is the most common methodology to yield H₂ gas using water as a clean and renewable
64 energy resource. Electrolysis has high product purity up to 99.9 vol%, this purity can be attained
65 on both scales large and small. The only setback is that electrolysis can also be responsible for the
66 emission of CO₂ gas if a non-renewable energy resource is used to produce the required
67 electrochemical energy [4,5]. The materials used to construct the electrolysis cell must also
68 withstand certain tough operating conditions and need further development in order to
69 commercialize this clean energy method for producing hydrogen gas as fuel. This clean fuel can
70 be yielded directly from splitting water using different techniques. These techniques include photo
71 electrochemical hydrogen production (photo electrolysis), thermochemical water splitting and

72 water electrolysis [6]. This study focuses on using electrolysis to split water into its core
73 constituents of H₂ and O₂ gas respectively [7].

74

75 Three main methods are currently under consideration for the production of hydrogen via water
76 electrolysis: proton exchange membrane [8], solid oxide cell and alkaline melt. The
77 electrochemical cell of alkaline electrolysis comprises of an alkaline aqueous electrolyte, two
78 electrodes and a microporous separator for ion conduction. The hydroxyl ions generated at cathode
79 electrode are migrated to anode and the remaining H⁺ ions at the cathode electrode combine with
80 electrons to form H₂ gas [9]. The two electrodes are cathode and anode from which the cathode
81 metal possesses a good catalytic activity and the anode electrode possesses an oxide coating layer.
82 The molten melts of NaOH and KOH are applied as electrolyte solutions. The ion-conducting
83 microporous separator permits the movement of hydroxyl ion and restricts the involvement of
84 produced oxygen and hydrogen. The efficiency of alkaline electrolysis can reach up to 70% [10].

85

86 Electrochemical studies focused on molten hydroxides for the generation of hydrogen fuel via
87 water splitting were demonstrated by Licht et al. and Al-Shara et al. [11,12]. These studies
88 investigated various mixed and pure alkali hydroxides as electrolytes such as Ba(OH)₂, KOH,
89 LiOH, NaOH at temperatures between 200 and 700 °C. The applied voltage range was maintained
90 between 1.1 and 2.3 V using a nickel and platinum metal as an anode and a nickel plate as a cathode
91 respectively. It is also mentioned that molten hydroxides act as catalyst, therefore there is no need
92 for any additional heat [12]. A detailed study was performed by Nagai et al. [13], which focused
93 on H₂ production potentials and efficiency of the electrochemical cell with Ni-Cr-Fe alloy as a
94 cathode material, under atmospheric pressure and using 10 wt% of KOH aqueous solution.

95
96 Licht et al. [14] reported an electrochemical study for the generation of ammonia from steam and
97 air via an equimolar ratio of molten NaOH-KOH with suspended nano-Fe₂O₃ particles using nickel
98 electrodes at a temperature of 200 °C and an applied voltage of 2 V. Ganley [15] studied direct
99 electrolysis by using experimental conditions of 18 M of KOH, 400 °C temperature, 8.7 MPa
100 partial pressure, fixed cathode of monel alloy and variable anodes (cobalt-plated nickel, lithiated
101 nickel, monel alloy and nickel). At temperatures as low as 80 °C, the study of Anani et al. [16]
102 discovered a technique to produce high purity hydrogen gas at cathode while maintaining high
103 current efficiency during the electrolysis of hydrogen sulphide. The intermediary solution resulting
104 in the generation of latter contained an equimolar concentration of NaOH and NaHS at
105 experimental temperature. Two-electrode electrolysis process has been used in this study to apply
106 a voltage to the cathode and anode to split steam through eutectic molten hydroxide. Subsequently,
107 O₂ and H₂ gases were collected from anode and cathode compartment respectively. Hydrogen gas
108 was detected by using a hydrogen gas tube and hydrogen gas sensor where the actual rate of H₂
109 gas yield was measured using pneumatic trough method.

110
111 There are limited studies that have been carried out on how the electrochemical process occurs
112 through the steam splitting with the help of molten salt's solution for H₂ gas production. Therefore,
113 this study aims to record an escalation in the efficiency of H₂ gas production by optimizing several
114 operating parameters such as temperature and applied voltage or by changing the material used for
115 cathode or anode construction in the electrochemical cell. The electrochemical analyses were
116 performed by using graphite and stainless anodes and platinum, stainless steel and nickel cathodes.
117 From literature it is analyzed that Ni, Pt and St.st metals were suitable for electrolysis because they

118 are stable under highly alkaline solution, low cost, easily available [17,18]. Fifty four combinations
119 of cathode, anode along with different operating variables have been tested for the production of
120 H₂ gas through the splitting of steam via molten hydroxide salt. This is a comparative study to find
121 out the most efficient electrochemical cell that increase the efficiency of steam splitting through
122 electrolysis of eutectic molten hydroxide. All these electrochemical investigations were carried out
123 at 225 to 300 °C temperature and 1.5 to 2.5 V applied voltage values.

124 **2. Experimental**

125 *2.1. Two-electrode electrolysis*

126 A mixture of 300 g of NaOH-KOH (49–51 mol%) was used as a electrolyte and placed inside
127 retort before being heated to a temperature of 300 °C for 24 h. The retort has already been placed
128 inside the pore of a vertical tube furnace. A pure alumina crucible was used to hold the mixture of
129 hydroxide salt. Stainless steel, platinum and nickel were used as cathode, whereas stainless steel
130 and graphite were used as anode during the experiments. Prior to immersing cathode and anode
131 inside the eutectic molten hydroxide to begin electrolysis, each electrode was placed inside an
132 alumina tube of 20 mm inside diameter.

133
134 The reason for covering electrodes with an alumina tube was to prevent the mixing of H₂ gas with
135 O₂ gas formed as a result of the electrolysis process. This compartment should be tightly sealed to
136 avoid any gas leakage. The diameters of different electrodes used in this study and their areas are
137 listed in Table 1. The total duration of the steam electrolysis process was approximately 1800 s
138 after that hydrogen gas was collected. Direct current (DC) source of power was used for voltage
139 applications on both electrodes.

140

141 This applied voltage was altered between 1.5 and 2.5 V. It is worth mentioning that although the
142 voltage is listed as being positive, however, the negative terminal of DC source was actually
143 connected to the cathode. Therefore, the polarity of this electrode in reality is negative.

144 **2.2. Steam generation**

145 Before the electrolysis process was performed, a combination of argon gas and steam was
146 introduced to the eutectic molten hydroxide. Argon gas worked as a carrier for steam introduction
147 into the bottle. In this study, steam was generated by placing a 500 mL dreschel bottle filled with
148 300 mL of distilling water on a hot plate heater. The temperature of the hotplate can be varied from
149 the insert temperature button. The argon gas inlet stream was connected to the inlet of the dreschel
150 bottle head which was directly dipped into hot distilled water. Then, argon gas left the dreschel
151 bottle from the outlet head. The stream of argon gas loaded with steam was connected to a ceramic
152 tube which was then submerged in molten hydroxide [19].

153
154 Distilled water was heated up to 70 °C. The argon gas stream bubbled through the hot water and
155 left the bottle loaded with water vapor. This was then introduced directly to the molten hydroxide.
156 The humidity of the argon gas was about 50%, when it left the dreschel bottle at a temperature of
157 70 °C and a flow rate of 40 cm³ min⁻¹. The steam flow rate was about 7.28 cm³ min⁻¹ that was
158 calculated using Dalton's law for gases. The residence time required to achieve saturation between
159 eutectic molten hydroxide and humid mixture of argon gas was influenced by salt volume in the
160 crucible. The residence time needed to achieve the saturation between eutectic molten hydroxide
161 and the flow rate of humid argon gas was between 2–6 min.

162 **2.3. Hydrogen gas production analysis**

163 The start of H₂ gas generation at cathode was detected by using a Gastec gas detector tube. This
164 gas tube detector is capable of measuring up to 2 vol% of hydrogen gas. Thin glass tubes are
165 usually available with outer calibration scales. These calibration marks help them to measure the
166 concentrations directly [20]. Tubes undergo stringent quality control with each production
167 percentage independently tested and calibrated.

168
169 A hydrogen gas sensor pro-gasbadge was also used to detect hydrogen gas produced up to 2000
170 ppm. This sensor has an interchangeable “smart” sensors monitor for hydrogen gas. There is a
171 direct communication between the sensor and the Docking Station with the help of an infrared
172 interface. As gas produced at cathode was confirmed as hydrogen gas, the production rate was
173 measured using water displacing method (Pneumatic Trough) and calculated as an actual gas rate
174 using Dalton’s law for gases. The hydrogen gas production rate due to steam splitting via
175 electrolysis of eutectic molten hydroxide was calculated using Eq. (1):

176
177
$$\text{Production rate} = \frac{\text{Mass of H}_2 \text{ produced}}{(\text{Immersed area of cathode} \times \text{Duration of H}_2 \text{ production})} \times 100\% \quad (1)$$

178
179 The values that were inserted into this equation were determined as follows. The mass of H₂ gas
180 production was found from the multiplication of molecular weight and actual number of moles of
181 H₂ gas. The actual number of moles can be measured using the equation of state of gases at a
182 temperature of 25 °C, partial pressure of hydrogen gas and actual volume of hydrogen. The partial
183 pressure of hydrogen was calculated using Dalton’s law for gases at 25 °C and 1 atm. The actual
184 volume of hydrogen gas was calculated by multiplying the mole fraction of hydrogen gas by total

185 volume of collected gas during the electrolysis process from cathode compartment using water
186 displacement method. As for the current efficiency of hydrogen gas production, this was calculated
187 using Eq. (2):

188

$$189 \quad \text{Current efficiency} = \frac{\text{Charge needed to produce H}_2 \text{ in theory}}{\text{Charge passed during electrolysis}} \times 100\% \quad (2)$$


190

191 The values that were inserted into this equation were determined as follows. The amount of electric
192 charge (Q) passing through the electrolytic mixture during hydrogen gas production can be
193 obtained by integrating the current time plots. To calculate the charge needed to produce hydrogen
194 gas in theory, the number of electrons involved to split steam to hydrogen gas
195 was multiplied by the Faraday constant (96485 C/mol) and the number of moles of hydrogen gas
196 produced. Thus, higher electric charge flow indicates more hydrogen gas produced at cathode.

197 **3. Results and discussion**

198 The minimum amount of voltage and overall amount of electrical energy needed for the generation
199 of H₂ gas from water splitting at 25 °C temperature is 1.23 V [21]. The net reaction of water
200 splitting can be represented as in Eq. (3):

201



203

204 In practice, because of the bubble formation, low reaction rate and activation energy barrier of
205 reaction, the electrochemical cell voltage needs to be larger than the required cell voltage.
206 Therefore, in this study, the cell voltages used were kept above the minimum cell voltage of 1.23

207 V even though it needs to be lower than this minimum value at high operating temperatures. The
208 higher applied voltages between 1.5 and 2.5 V to split water were arranged in such an order to
209 overcome any barrier for the electrolysis process and to ensure continuous hydrogen gas
210 production. The electrolysis process was operated in a temperature range between 225 and 300 °C.

211 ***3.1. Performance of stainless steel anodic cell***

212 Stainless steel was employed as anode material in the electrolysis process. Therefore it should be
213 mentioned that when it was employed at high temperatures in the eutectic molten hydroxide, it had
214 a passivate type behavior even though it was used in a corrosive environment [22]. The stainless
215 steel anode undergoes passivation with the creation of an outer layer shield, and there is no
216 influence on the response of current-time plot which is directly reflected in the rate of hydrogen
217 gas formation. These results were repeatedly obtained for four times over and thus noises were not
218 caused by experimental errors. The noise, as mentioned earlier was due to steam splitting and the
219 development of bubbles on the surface near nickel cathode.

220
221 Ni, Pt and St.st electrodes were used individually as cathode in the designed electrochemical cell,
222 to study the electrolysis and resultantly hydrogen production [23], against St.st anode. The other
223 applied conditions were changed continuously to find the optimum ones, including temperature
224 and voltage. Fig. 1 shows the current-time responses at operating temperature 300 °C. At this
225 operating temperature, different voltages were applied (1.5, 2.0 and 2.5 V). These electrolysis
226 processes were carried out as mentioned previously, under a steady argon gas flow rate of 40 cm³
227 min⁻¹ and a fixed steam flow of 7.23 cm³ min⁻¹. The reason for this comparison is to find out the
228 most efficient cathode material during the electrochemical process for a higher rate of hydrogen
229 gas production.

230 In addition to nickel, platinum metal was also selected as a cathode for the hydrogen evolution in
231 the eutectic molten hydroxide [24]. The recorded current-time plots for all the tested combinations
232 are shown in comparison against St.st anode in Fig. 1 at different applied voltages. As mentioned
233 previously, platinum is a precious metal and this prevents it from large scale industrial use, as well
234 as limiting its usage for laboratory scale investigations. In this study, a platinum wire of 0.5 mm
235 diameter was used. Since the diameter of the used platinum is very small, it was necessary to
236 increase the surface area that was exposed to the electrolyte to be approximately the same as the
237 nickel electrode surface area. This was done to ensure a smooth comparison of current flow and
238 production rate of hydrogen gas at same operating conditions. Therefore, in order to achieve a
239 surface area of 2.55 cm^2 , it was simply rolled into a spiral shape with 15 cm of wire length. This
240 increase in the surface area significantly contributed to increase the current flow value at different
241 applied voltages.

242

243 It can be observed from the current-time plots @ St.st anode that current flow increases with an
244 increase in the applied voltage at applied operating temperatures. After electrolysis, no change can
245 be observed on Pt electrode's surface. The reason for no change in the surface area of electrode is
246 because platinum is an inert metal and does not inhibit the reaction occurring at its surface. It
247 simply acts as a means to transfer electric charge from power supply to the electrolyte without
248 undergoing any change. Platinum can also be classified as a corrosion resistance metal to
249 specifically withstand sodium hydroxide melt under suitable conditions [25].

250

251 Stainless steel metal was also used as a cathode in the eutectic molten hydroxide to compare with
252 other tested materials at same operating conditions. It can be observed from Fig. 1 that the current

253 increases with an increase in the applied voltage. It is observed that at 225 °C, the current response
254 is stable and the current increases approximately with an increment of 0.2 A for every 0.5 V
255 increase in the applied voltage. This observed phenomena of the current at 225 °C is not applicable
256 when the temperature is increased to 300 °C. However, when temperature increases, the current
257 response curve begins to appear noisy, particularly at higher applied voltages. The escalation in
258 the production of molecules of H₂ gas around cathode is mainly liable for this noisy response of
259 the current-time plot. Further surface morphology can be considered for this in future for more
260 comprehensive analysis.

261
262 The important point that can be observed from the results of current time plot is that the overall
263 recorded current is the highest while using nickel as cathode material during electrolysis inside the
264 eutectic molten hydroxide might because of its good catalytic potentials [26]. These observed
265 results are consistent for the nickel electrode at different applied voltages and different operating
266 temperatures. Furthermore, for nickel electrode, when the applied voltage increases from 1.5 to
267 2.5 V, the current increased accordingly as confirmed from the mentioned plots and are in
268 accordance with the literature [27].

269
270 During testing, it was also observed that at 225 °C the current increases from 0.2 to 1.4 A at an
271 applied voltage of 1.5 to 2.5 V respectively. For stainless steel and platinum electrodes, the
272 recorded current-time plots show that their current responses are approximately same at different
273 applied voltages and different operating temperatures. While at 300 °C temperature, the current is
274 recorded comparable, little bit higher for St.st than Ni at 1.5 and 2 V. It should be noted here that
275 the steam and argon mixture was bubbled inside the eutectic molten hydroxide for an approximate

276 duration of 600–900 s before the electrolysis process was started. From these plots obtained during
277 electrolysis, the current flow observed was with some level of noise in most conditions. This noise
278 observed is quite typical during electrolysis of steam via eutectic molten hydroxide and during the
279 formation of hydrogen gas bubbles around the cathode.

280

281 When hydrogen molecules are formed, they migrate away from the cathode in order to allow other
282 steam molecules to be split into forming new hydrogen molecules along with the oxygen. This
283 transfer of hydrogen and steam molecules to and from the nickel cathode surface during
284 electrolysis process can be listed a possible reason for the noise noticed in the current-time plot. It
285 is significant to mention here that the nickel cathode is highly stable for molten hydroxide water
286 splitting as stated by literature [11] that corroborates with these research findings.

287 *3.1.1. H₂ gas production potentials @ anodic stainless steel cell*

288 The production of H₂ gas was analysed using three methods, including gascotec gas detector tube,
289 hydrogen gas sensor (PRO-GASBADGE) and water displacement method. The gas sensor
290 monitored the hydrogen gas produced up to 2000 ppm. The hydrogen gas sensor detected the
291 hydrogen gas between 655 to 705 ppm at an applied voltage of 1.5 V and more than 2000 ppm at
292 an applied voltage of 2 V to the electrolysis cell. This also confirmed that the only gas produced
293 at the cathode is hydrogen. To quantify the amount of hydrogen gas produced at cathode, the gas
294 flow was collected in a measuring cylinder using water displacement method. The hydrogen gas
295 was collected and measured over a period of 10 minutes intervals.

296

297 The process was repeated four times and the production rate remained approximately constant.

298 Fig. 2 shows the rate of hydrogen gas production at different cathodes (Ni, Pt, and St.st) at different

299 operating temperatures and different applied voltages. It is clear from this data that a steady
300 increase in the hydrogen gas production rate at cathode can be noticed with an increase in the
301 operating temperature and applied voltage. This trend is valid for all examined cathode materials.
302 Furthermore, the flow rate of hydrogen gas using a nickel electrode recorded the highest value in
303 comparison to the other two used cathode materials i.e. stainless steel and platinum in this order
304 respectively. For example, the hydrogen gas flow rate at 250 °C and applied voltage of 2 V using
305 a nickel, stainless steel and platinum cathode were 5.0, 3.5, 3.0 cm³ min⁻¹ respectively. These
306 results indicate that nickel has an enhanced level of catalytic activity in the current eutectic molten
307 hydroxide, contributing towards splitting the steam with higher efficiency. The hydrogen gas
308 production rates were calculated with Eq. (1).

309 *3.1.2. Current efficiency of the cell*

310 The calculated current efficiency of hydrogen gas production using Eq. (2) is presented in Fig. 3
311 using different cathode materials at different operating temperatures and applied voltages. It is
312 obvious from the results that the current efficiency of hydrogen gas production rate using a nickel
313 cathode reached up to 90.5% at 300 °C. This achieved value of efficiency shows that the value of
314 current in practical was approximately close to the value of the current in theory. Alternately, when
315 platinum was used as a cathode, the current efficiency of hydrogen gas production rate decreased
316 with an increase in the temperature.

317
318 This implies that the platinum catalytic activity decreased to allow the reaction to occur with
319 increasing temperature. The achieved current efficiency at 225 °C was about 107.5%. The reason
320 for being the value of the current efficiency above 100% was due to the experimental error or other
321 side reactions happened. When stainless steel was used as cathode against same anode the

322 efficiency reached up to 90%. When interpreting the hydrogen gas production rate and current
323 efficiencies, different factors that need to be taken into account are ionic transfer and gas bubble
324 behavior in the electrolyte. These factors, in turn, influence the current during electrolysis. The
325 transfer of ions is measured from the flow field and viscosity of the electrolyte solution. With the
326 development of electrolysis process, viscosity increases as a result of electrolyte concentration.
327 That's why constant steam addition is carried out to preserve a constant viscosity and concentration
328 of the electrolyte [28,29]. Yet, greater transport does not mean greater H₂ generation but it is right
329 to say that it is associated with fast reaction rates. The more the reaction rate, the more will be the
330 bubbles formed, and this can adversely obstruct interaction of electrolyte solution with electrode
331 material [29]. For future work, to speed up the exit of bubbles and eliminate them from the
332 respective electrode compartment, the recirculation approach can be mechanically applied to
333 electrolytes.

334 *3.2. Performance of graphite anodic cell*

335 Further electrochemical investigation undertaken in the eutectic molten hydroxide used graphite
336 as a material for anode and alternates between nickel, platinum and stainless steel as a cathode.
337 The reason for using graphite in place of stainless steel in this study is to compare the effect of
338 changing anode material on the electrolysis cell performance. Specifically, it must be investigated
339 whether it has a direct effect on the hydrogen gas production rate and the current efficiency. This
340 cell performance was also tested at different operating temperatures and different applied voltages.
341 The current-time plot shown in Fig. 4 is noted at 300 °C. These electrolysis processes were
342 performed for 1800 s under argon gas atmosphere. It is observed that the plots of current response
343 using nickel and stainless steel electrodes are approximately similar at operating temperatures of
344 225 °C and 250 °C with applied voltages of 1.5 and 2.0 respectively.

345

346 Alternately, when the operating temperature of eutectic molten hydroxide is raised to 300 °C, the
347 current response using a nickel cathode becomes higher than for stainless steel cathode. This
348 difference between the former and latter is approximately 0.2 A and 0.4 A at 2.0 V and 2.5 V
349 respectively as shown in Fig. 4. On the other hand, the current response using a platinum cathode
350 is recorded as the lowest among the three different materials at different operating temperatures
351 and applied voltages respectively.

352

353 The electro-activity of nickel cathode increased during electrolysis with increasing temperature.
354 Platinum, however showed no change in its electro activity even when the operating temperature
355 of eutectic molten hydroxide or the applied voltages was increased respectively. These findings
356 can be considered as a promising for potentially novel, green technology aiming to produce
357 hydrogen gas using cheap, untreated metal instead of precious platinum metal. The collection of
358 the gas using water displacement method was carried out for 10 min and repeated twice to confirm
359 the accuracy of the gas production rate.

360 *3.2.1. H₂ gas production potentials @ anodic graphite cell*

361 The hydrogen gas flow rate increases with an increase in the operating temperatures of eutectic
362 molten hydroxide and with increasing applied voltage during electrolysis, as seen in Fig. 5. For
363 nickel cathode, the hydrogen gas flow rate produced during electrolysis at 300 °C and an applied
364 voltage of 2.5 V, records the highest flow rate followed by stainless steel and platinum under same
365 operating conditions. Alternately, the nickel electrode electro-activity for producing hydrogen gas
366 reduces at a low temperature of 225 °C and at an applied voltage of 1.5 V to be lower than the
367 stainless steel electrode gas flow rate at the same operating conditions, as seen in Fig. 5 [30]. While

368 comparing the hydrogen gas flow rate for both anodes made of stainless steel and graphite using
369 different cathode metals, no significant change can be observed as seen in Figs. 2 and 5.

370



371 It is still imperative to mention that when graphite is used as an anode, the reduction process can
372 possibly be obstructed by carbon particles blocking the pores of oxide. This can prevent electrolyte
373 contact with oxide and significantly hamper the overall electrolytic process as mentioned by Cox
374 A. et al., [31]. Therefore, it is important to take care when using graphite repeatedly to avoid
375 contaminating the electrolyte and contributing to unfavorable side reactions. The production rate
376 for each electrode was calculated using Eq. (1). The production rate for hydrogen gas increases
377 with an increase in the operating temperature of eutectic molten hydroxide. The platinum cathode
378 did not exhibit this behavior because its production rate decreases with increasing temperature.
379 This behavior was seen even when stainless steel was used as an anode. The production rate of
380 hydrogen gas decreases when the temperature increases to 300 °C. This result leads to the
381 conclusion that electro-activity of platinum metal inside the eutectic molten hydroxide decreases
382 with increasing operating temperature.

383 *3.2.2. Current efficiency of the cell*

384 Fig. 6, presents the range and the average calculated values of current efficiency for the
385 electrochemical cell using different cathode materials at different operating temperatures. The
386 current efficiency of hydrogen gas production decreases with an increase in the operating
387 temperature of the eutectic molten hydroxide. For example, as temperature increases from 225 to
388 300 °C, the current efficiency decreases from 101.6 to 68.0% using nickel metal as cathode and
389 graphite as anode. The reason for being the current efficiency about 101.6% at 225 °C using nickel
390 cathode can be explained as an experimental error. For use stainless steel and platinum cathodes,

391 the current efficiencies were 115.3% and 102.3% respectively at 225 °C. The reason for being the
392 current efficiency more than 100% is an experimental error at this specific operating temperature.
393 The reason for decrease in current efficiency for hydrogen generation with an increased
394 temperature of eutectic molten hydroxide is because the formation of superoxide O_2^- reduction
395 increases and subsequently competes with the hydrogen formation reaction [11] as seen in Eqs.
396 (4) and (5):

397



400

401 These findings relating to a decrease in current efficiency with increasing temperature and applied
402 voltage is not in agreement with the current efficiency findings for hydrogen gas production using
403 stainless steel as an anode. The only exception to this rule was using platinum as a cathode. In
404 conclusion, the current efficiency increases with an increase in operating temperature of eutectic
405 molten hydroxide (for all cathode materials) and increasing the applied voltages in case of using
406 either nickel or stainless steel as cathode during electrolysis.

407 **4. Conclusions**

408 This study finds that steam splitting assisted the eutectic molten hydroxide electrolysis at high
409 operating temperatures for hydrogen gas production is a way forward to reduce applied voltages.
410 For nickel cathode, an increase in current directly affected the hydrogen gas flow rate at cathode.
411 Comparatively Ni cathode against stainless steel anode proved a good combination. The achieved
412 current efficiency for Ni, increased from 63.2 to 90.5% with an increase in the operating
413 temperature from 225 to 300 °C respectively. For platinum cathode, the flow rate of hydrogen gas

414 production increased from 1.6 to 4.5 cm³ min⁻¹ with an increase in the applied voltage from 1.5 to
415 2.5 V at 300 °C. For stainless steel cathode and anode, the hydrogen gas flow rate also increased
416 from 2 to 7 cm³ min⁻¹. However, when graphite anode was used during electrolysis, the response
417 of current increased with an increase in the operating temperature. The subsequent production rate
418 also increased, but the current efficiency decreased with an increase in the operating temperature
419 for all three cathode materials. This behaviour can be attributed to the carbon particles that obstruct
420 the reduction process by blocking the pore of the oxide and preventing oxide from coming in
421 contact with electrolyte. Cost effective electrode material with good stability and catalytic nature
422 electrolyte will be a good option for the anodic electrode under these conditions for H₂ gas
423 production.

424 **Acknowledgment**

425 The authors are grateful for the financial supports from the EPSRC (EP/J0 0 0582/1 and
426 EP/F026412/1), and Ningbo Municipal People's Government (3315 Plan and 2014A35001-1).

427 **References**

- 428 1. H. Yüksel, A. Özbay, M. Kahraman, R. Solmaz, *Int. J. Hydrogen Energy* 43 (23) (2018)
 429 10586–10594.
- 430 2. I. Dincer, C. Acar, *Int. J. Hydrogen Energy* 40 (34) (2015) 11094–11111.
- 431 3. C. Acar, I. Dincer, *J. Clean. Prod.* 218 (2019) 835–849.
- 432 4. R. Kothari, D. Buddhi, R. Sawhney, *Renew. Sust. Energ. Rev.* 12 (2) (2008) 553–563.
- 433 5. E. Cuce, Z. Nachan, P.M. Cuce, F. Sher, G.B. Neighbour, *Intl. J. Ambient Energy.* 40 (1)
 434 (2019) 86–95.
- 435 6. C. Mansilla, J. Sigurvinsson, A. Bontemps, A. Maréchal, F. Werkoff, *Energy.* 32 (4) (2007)
 436 423–430.
- 437 7. N.K. Al-Shara, F. Sher, A. Yaqoob, G.Z. Chen, *Int. J. Hydrogen Energy.* 44 (50) (2019)
 438 27224–27236.
- 439 8. T. Kato, M. Kubota, N. Kobayashi, Y. Suzuoki, *Energy.* 30 (14) (2005) 2580–2595.
- 440 9. D. Ipsakis, T. Kraia, M. Konsolakis, G. Marnellos, *Renew. Energy.* 125 (2018) 806–818.
- 441 10. M. Balat, *Int. J. Hydrogen Energy.* 33 (15) (2008) 4013–4029.
- 442 11. S. Licht , S. Liu , B. Cui , J. Lau , L. Hu , J. Stuart , B. Wang , O. El-Ghazawi , F.-F. Li, J.
 443 *Electrochem. Soc.* 163 (10) (2016) 1162–1168.
- 444 12. N.K. Al-Shara , F. Sher , S.Z. Iqbal , Z. Sajid , G.Z. Chen ,*J. Energy Chem.* 49 (2020) 33–
 445 41.
- 446 13. N. Nagai, M. Takeuchi, T. Kimura, T. Oka, *Int. J. Hydrogen Energy.* 28 (1) (2003) 35–41.
- 447 14. S. Licht, B. Cui, B. Wang, F.-F. Li, J. Lau, S. Liu, *Science.* 345 (6197) (2014) 637–640.
- 448 15. J.C. Ganley, *Int. J. Hydrogen Energy.* 34 (9) (2009) 3604–3611.
- 449 16. A. Anani , Z. Mao , R.E. White , S. Srinivasan , A. Appleby , *J. Electrochem. Soc.* 137 (9)
 450 (1990) 2703–2709.
- 451 17. P.A. Selembo, M.D. Merrill, B.E. Logan, *J. Power Sources.* 190 (2) (2009) 271–278.
- 452 18. A.K. Chaurasia, H. Goyal, P. Mondal, *Int. J. Hydrogen Energy.* (2019).
- 453 19. R. Hino, K. Haga, H. Aita, K. Sekita, *Nucl. Eng. Des.* 233 (1-3) (2004) 363–375.
- 454 20. K.H. Kim, A. Farooq, M.Y. Song, S.-C. Jung, K.-J. Jeon, J. Song, C.H. Ko, J. Jae, Y.-K.
 455 Park, *J. Environ. Manage.* 232 (2019) 330–335.
- 456 21. X. Du , W. Liu , Z. Zhang , A. Mulyadi , A. Brittain , J. Gong , Y. Deng , *Chem. Sus.*
 457 *Chem.* 10 (5) (2017) 847–854.
- 458 22. B. Bozzini , S. Barella , F. Bogani , G. Giovannelli , S. Natali , G. Scarselli , M. Bo-
 459 niardi , *Mater. Corros.* 63 (11) (2012) 967–978.
- 460 23. Y. Bicer, I. Dincer, *ACS Sustain. Chem. Eng.* 5 (9) (2017) 8035–8043.
- 461 24. K. Guo, A. PrévotEAU, K. Rabaey, *J. Power Sources.* 356 (2017) 484–490.
- 462 25. R. Chen, C. Yang, W. Cai, H.-Y. Wang, J. Miao, L. Zhang, S. Chen, B. Liu, *ACS Energy*
 463 *Lett.* 2 (5) (2017) 1070–1075.
- 464 26. M. Zhou , Q. Weng , Z.I. Popov , Y. Yang , L.Y. Antipina , P.B. Sorokin , X. Wang , Y.
 465 Bando , D. Golberg , *ACS Nano.* 12 (5) (2018) 4148–4155.
- 466 27. W. Cai, W. Liu, J. Han, A. Wang, *Biosens. Bioelectron.* 80 (2016) 118–122.
- 467 28. W. Doenitz , R. Schmidberger , E. Steinheil , R. Streicher , *Int. J. Hydrogen Energy.* 5 (1)
 468 (1980) 55–63.
- 469 29. R.F. De Souza , J.C. Padilha , R.S. Gonçalves , M.O. De Souza , J. Rault-Berthelot , J.
 470 *Power Sources.* 164 (2) (2007) 792–798.

- 471 30. A.G. Vidales, K. Choi, S. Omanovic, *Int. J. Hydrogen Energy*. 43 (29) (2018) 12917–
472 12928.
473 31. A. Cox, D.J. Fray, *J. Appl. Electrochem.* 38 (10) (2008) 1401–1407.
474

475

476

List of Tables

477


Table 1. Dimensions of the electrodes.

Electrode material	Diameter (cm)	Depth (cm)	Surface area (cm ²)
Nickel	0.50	1.50	2.55
Platinum wire	0.05	1.50 × 10.80	2.55
Stainless steel	0.50	1.50	2.55
Graphite	1.00	1.50	5.50

478


479

List of Figures




481


482 **Fig. 1.** Current-time plots @ stainless steel anode vs Ni, Pt, and St.st cathodes recorded for 1800
483 s electrolysis at a temperature of 300 °C and applied voltages of 1.5, 2.0 and 2.5 V.



484




485



486


487 **Fig. 2.** Hydrogen gas production rate versus applied voltages at various operating temperatures;
 488 *T1* (225 °C), *T2* (250 °C) and *T3* (300 °C) with St.st anode and different cathode materials; (a) Ni,
 489 (b) Pt and (c) St.st.

490



491
 492
 493 **Fig. 3.** Current efficiency of electrochemical cell for hydrogen gas production at different
 494 operating temperatures; T_1 (225 °C), T_2 (250 °C) and T_3 (300 °C) with St.st anode.

495




496



497 **Fig. 4.** Current-time plots @ graphite anode vs. Ni, Pt and St.st cathodes recorded for 1800 s
 498 electrolysis at 300 °C temperature with different applied voltages; 1.5, 2.0 and 2.5 V.

499

500
501




502
503



504
505 **Fig. 5.** Hydrogen gas production rate versus applied voltages at different operating temperatures;
506 T1 (225 °C), T2 (250 °C) and T3 (300 °C) with graphite anode and various cathode materials; (a)
507 Ni, (b) Pt and (c) St.st.

508
509
510




511
512
513 **Fig. 6.** Current efficiency of the electrochemical cell for hydrogen gas production at different
514 operating temperatures; T_1 (225 °C), T_2 (250 °C) and T_3 (300 °C) with graphite anode.
515

516 **Graphical abstract**

517 Various combinations of cathode, anode, temperature and voltage have been tested for
518 optimization of best working conditions with molten hydroxide for H₂ gas production. Steam
519 splitting is an encouraging alternate methodology for H₂ fuel production.

520



521

522